

# Executive 70S-6 CC

*Executive*  
FILLER METALS

**A copper coated S6 wire where consistency, reliability and exceptional value is required.**

Executive 70S-6 CC is your best choice when consistency, reliability and exceptional value is required. It contains additional de-oxidizers that allow better wetting, flatter beads, faster travel speeds, and is the superior choice to other wire options.

Executive 70S-6 CC operates effectively with CO<sub>2</sub> or Argon mixed gas and is optimized for welding steels with moderate amounts of scale or rust.

Executive 70S-6 CC wire chemistry conforms to AWS/SFA 5.18 and is certified for GMAW by the CWB to classification B-G 49A 3 C1 S6 of CSA Standard W48.

## Advantages

- CMTR's provided by heat/lot with actual analysis
- Uniform copper coating extends life of consumable MIG parts
- Produces lower fume levels than standard wires

## Executive 70S-6 CC

### TYPICAL CHEMICAL COMPOSITION

CLASSIFICATION	C	Cr	Ni	Mo	Mn	Si	P	V	S	Cu	Yield Strength (mPa)	Tensile Strength (mPa)	Elongation %	CVN -30°C (-22°F)
ER70S-6	0.08	0.03	0.02	0.01	1.5	0.85	0.01	0.005	0.01	0.03	460	520	30	92 J 70 (ft-lb)

### TYPICAL MECHANICAL PROPERTIES AS WELDED

Executive 70S-6 CC is available in .035", .045" on 44-lb spools, 550-lb drums and GTAW as 70S-6 CCP, copper coated 36" lengths stamped on both ends for positive identification. \*A variety of sizes and packaging options are available upon request.

Wire chemistry conforms to AWS/SFA 5.18, Class ER70S-6 and is certified for GMAW by the CWB to classification B-G 49A 3 C1 S6 of CSA Standard W48.